

VISUAL INSPECTION PROFORMA – BLANKETS (2-PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Quality Contractors	M/s Excel Tex Industries (Pvt) Ltd	M/s Harmain Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (165 x 238 cm)	C (163 x 239 cm)
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Worldwide Logistics	M/s Alizeh Enterprises	M/s White Rose Trading
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (164 x 238 cm)	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	NC
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Non-Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Majid Traders	M/s Paramount Tarpaulin Industries	M/s Maris Intl (Pvt) Ltd
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (162 x 239 cm)	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	NC	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s H.Nizam Din & Sons	M/s Mahroz Textile	M/s Altaf Sons
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (159 x 231 cm)	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Sabri Textile	M/s Saleem Trading Corporation	M/s Saad Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (162 x 239 cm)	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Hussain Enterprises	M/s Al-Farooq Enterprises	M/s Ali Trading Corporation
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (162 x 237 cm)	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s M.M Musa Gee	M/s Pearl Associates	M/s Arneca International
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (163 x 240 cm)	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Marshall Enterprises	M/s FTS International (Pvt) Ltd	M/s Aryian's International
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (161 x 240 cm)	C	NC (162 x 238 cm)
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Non-Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s Active Vision (Pvt) Ltd	M/s Inovative Apparels
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s Sanauallah Textile Mills	M/s Usman Traders
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (164 x 237 cm)	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance

VISL INSPECTION PROFORMA – BLANKETS (2-PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s ALM Textile	M/s Blue Star International
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s Zeb & Company	M/s Nadir Saidjan Industries
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (2-PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Cops Enterprises	M/s Zahra Tents Industries (Pvt) Ltd	M/s Bataan Group of Services
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Pak Business International (Pvt) Ltd	M/s Awan Traders	M/s Bilal & Sons Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C	NC (159 x 240 cm)
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Compliance	Non-Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (2-PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s The Trade	M/s Shabbir & Sons	M/s Pak Rose Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (2-PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Bilal International Enterprises	M/s Nexus Trading (Pvt) Ltd	M/s Global Associates
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C	C
2.	Dry weight 2.0 to 2.2 kgs.	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Compliance	Compliance

J. Durrani

DM Inspection (Log), NDMA
Co-opted Member

A. Iqbal

Deputy Director (CDRF), NDMA
Member

[Signature]

Director (Legal), NDMA
Member

[Signature]

Director (Log), NDMA
Secretary

Kautilya

Member (Ops), NDMA
President

VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Quality Contractors	M/s Excel Tex Industries (Pvt) Ltd	M/s Harmain Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (162 x 240 cm)	NC (163 x 238 cm)
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Non-Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Worldwide Logistics	M/s Alizeh Enterprises	M/s White Rose Trading
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (162 x 237 cm)	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	NC
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Non-Compliance

VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Majid Traders	M/s Paramount Tarpaulin Industries	M/s Maris Intl (Pvt) Ltd
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (162 x 239 cm)	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	NC	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s H.Nizam Din & Sons	M/s Mahroz Textile	M/s Altaf Sons
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (240 x 161 cm)	NC (159 x 231 cm)	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C (3.18 kg)	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Non-Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Sabri Textile	M/s Saleem Trading Corporation	M/s Saad Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (162 x 239 cm)	C	NC (165 x 238 cm)
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Non-Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Hussain Enterprises	M/s Al-Farooq Enterprises	M/s Ali Trading Corporation
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (162 x 238 cm)	NC (162 x 237 cm)	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Non-Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s M.M Musa Gee	M/s Pearl Associates	M/s Arneca International
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (163 x 240 cm)	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Marshall Enterprises	M/s FTS International (Pvt) Ltd	M/s Aryian's International
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (161 x 240 cm)	C	NC (162 x 238 cm)
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Non-Compliance

AS

VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s Active Vision (Pvt) Ltd	M/s Inovative Apparels
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s Sanaullah Textile Mills	M/s Usman Traders
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (165 x 233 cm)	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s ALM Textile	M/s Blue Star International
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms	
			M/s Zeb & Company	M/s Nadir Saidjan Industries
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C
3.	Color Slate Grey	C/NC	C	C
4.	Border piping	C/NC	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C
6.	No bad smell & irritation to skin	C/NC	C	C
7.	Cigarette proof / Ignition	C/NC	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C
10.	Hydraulic compressed	C/NC	C	C
*Compliance/Non-Compliance			Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Cops Enterprises	M/s Zahra Tents Industries (Pvt) Ltd	M/s Bataan Group of Services
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Compliance	Compliance

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Pak Business International (Pvt) Ltd	M/s Awan Traders	M/s Bilal & Sons Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	NC (168 x 238 cm)	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Non-Compliance	Compliance

D


VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s The Trade	M/s Shabbir & Sons	M/s Pak Rose Enterprises
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	NC (163 x 239 cm)	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Non-Compliance	Compliance	Compliance



VISUAL INSPECTION PROFORMA – BLANKETS (3 PLY)

Ser	NDMA STANDARD SPECIFICATIONS	C/NC	Name of Firms		
			M/s Bilal International Enterprises	M/s Nexus Trading (Pvt) Ltd	M/s Global Associates
1.	Size (Width x length) - 165 x 240 cm +-1	C/NC	C	C	C
2.	Dry weight 3.2 to 3.5 kgs	C/NC	C	C	C
3.	Color Slate Grey	C/NC	C	C	C
4.	Border piping	C/NC	C	C	C
5.	Manufacturing, marking and batch Number	C/NC	C	C	C
6.	No bad smell & irritation to skin	C/NC	C	C	C
7.	Cigarette proof / Ignition	C/NC	C	C	C
8.	NDMA Colour Logo on blanket (15 x 15 cm) & Carton (20 x 20 cm)	C/NC	C	C	C
9.	Packing (Polythene, wrapping & carton 5 ply)	C/NC	C	C	C
10.	Hydraulic compressed	C/NC	C	C	C
*Compliance/Non-Compliance			Compliance	Compliance	Compliance




 DM Inspection (Log), NDMA
 Co-opted Member




 Deputy Director (CDRF), NDMA
 Member



 Director (Legal), NDMA
 Member



 Director (Log), NDMA
 Secretary



 Member (Ops), NDMA
 President



ARMY STORES INSPECTION DEPOT LAHORE



LAB TEST REPORT

Page 1 of 3

Nomenclature	Fleece Blanket 3 Ply	Ref: No. 4219/ LAB/LID/
F/Note No.	F.3(9)/2024-25/NDMA (Proc) Dated 07-02-2025	
Nature of Sample	Outer Agency	Temp= 21°C
		Humidity= 65%
Date Receipt	18-02-2025	Date of Reporting
No of Sample	27 Nos	09 Apr 2025
Client Name:	M/S NDMA	

S#	DESCRIPTION	Quality					
		FTS	Arnecca	Results	Auzen	Maxis	
		A	B	C	D	E	
1	Material	Outer side	Polyester	Polyester	Polyester	Polyester	Polyester
		Filling material	Polyester	Polyester	Polyester	Polyester	Polyester
2	Nature of Dye	Dope	Dope	Dope	Disperse	Dope	
3	TOG Value (Clo Value)	3.6	4.2	2.5	3.2	3.7	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
5	Wt of complete blanket	3.3 kg	4.2 kg	3.9 kg	3.2 kg	2.2 kg	
6	Wt/sq mtr single layer	Filling material	246.4	362.1	296.5	208.8	212.6
7	Thickness (3 x layers) at 46 g wt (to be carried out before bailing)		5.7 - 6.0	6.6 - 7.5	9.5 - 10.1	5.7 - 6.3	5.2 - 5.9
8	Length		240 - 241	246 - 247	242 - 243	237 - 238	248 - 249
9	Width		165 - 166	167 - 168	163 - 164	162 - 163	175 - 176
10	Raising		Both side raised	One side raised	Both side raised	Both side raised	Both side raised
11	Tensile strength	One side	Av= 500N	Av= 720N	Av= 460N	Av=780 N	Av= 600N
		Other side	Av= 260N	Av= 270N	Av= 215N	Av= 250N	Av= 300N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.0	1.0	1.0	1.0
		Other side	1.5	0.5	1.5	1.0	0.5
13	Wt loss% (after 3 x consecutive machines washes at 30°C)		1.8	1.7	1.9	1.8	1.7
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4
		Dry	4	4	4	4	4
16	PH Value		7 - 8	7 - 8	7 - 8	7 - 8	7 - 8

RA-I
 Checked by
 (Naeem Nasir)

RA-I
 I/C Lab
 (Imran Maqbool)



ARMY STORES INSPECTION DEPOT LAHORE



S#	DESCRIPTION		ALM Results					Blue Star		Alfajero		Sakoon Redi			
			F	G	H	I	J	K	L	M	N	O	P	Q	R
1	Material	Outer side	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester
		Filling material	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester
2	Nature of Dye		Dope	Dope	Disperse	Dope	Dope	Dope	Dope	Dope	Dope	Dope	Dope	Dope	
3	TOG Value (Clo Value)		2.8	3.8	3.4	3.6	3.1	4.3							
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	
5	Wt of complete blanket		3.7 kg	3.4 kg	3.2 kg	3.6 kg	3.7 kg	3.5 kg							
6	Wt/sq mtr single layer	Filling material	275.2	205.6	201.2	215.5	269.9	277.7							
7	Thickness (3 x layers) at 46 g wt (to be carried out before bailing)		6.2 - 6.7	4.9 - 5.5	6.2 - 6.6	6.2 - 6.5	6.2 - 7.1	6.9 - 7.1							
8	Length		237 - 238	248 - 249	237 - 238	248 - 249	238 - 239	247 - 248							
9	Width		165 - 166	175 - 176	163 - 164	166 - 167	167 - 168	165 - 166							
10	Raising		Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised							
11	Tensile strength	One side	Av= 490N	Av= 590N	Av= 700N	Av= 660N	Av= 550N	Av=510 N							
		Other side	Av= 210N	Av= 280N	Av= 250N	Av=350 N	Av= 220N	Av= 230N							
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.0	1.0	1.0	1.5	1.0							
		Other side	1.0	0.5	0.5	1.0	1.0	0.5							
13	Wt loss% (after 3 x consecutive machines washes at 30°C)		1.8	1.9	1.7	1.8	1.9	1.8							
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4	4							
		Staining on Cotton	4	4	4	4	4	4	4						
		Staining on Polyester	4	4	4	4	4	4	4						
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4	4							
		Dry	4	4	4	4	4	4	4						
16	PH Value		7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8							

RA-I Checked by (Naeem Nasir) zebee company Nadis saidjan industry Cops zahra Tents Batagira RA-I Pak Business I/C Lab (Imran Maqbool)



ARMY STORES INSPECTION DEPOT LAHORE



vision *Matid* *PAK*
Results *Trades* *RASC*

S#	DESCRIPTION	Ali Topog Bilalqsons Shabbir Results						
		S	T	U	V	X	Y	
1	Material	Outer side	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester
		Filling material	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester
2	Nature of Dye	Dope	Dope	Dope	Dope	Dope	Dope	
3	TOG Value (Clo Value)	3.6	2.6	3.1	2.9	3.2	3.6	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
5	Wt of complete blanket	3.7 kg	3.7 kg	4.0 kg	3.4 kg	3.5 kg	3.4 kg	
6	Wt/sq mtr single layer	Filling material	223.4	266.9	280.1	240.5	207.3	248.1
7	Thickness (3 x layers) at 46 g wt (to be carried out before bailing)		5.6 - 5.9	6.8 - 7.5	5.7 - 6.4	5.7 - 6.4	7.2 - 8.2	6.2 - 6.4
8	Length		249 - 250	241 - 242	247 - 248	234 - 235	241 - 242	240 - 241
9	Width		181 - 182	165 - 166	165 - 166	164 - 165	165 - 166	167 - 168
10	Raising		Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised
11	Tensile strength	One side	Av= 640N	Av= 340N	Av= 560N	Av= 580N	Av= 510N	Av= 760N
		Other side	Av= 290N	Av= 190N	Av= 220N	Av= 210N	Av= 180N	Av= 280N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.0	1.0	1.0	1.0	1.0
		Other side	0.5	1.0	0.5	0.5	1.0	0.5
13	Wt loss% (after 3 x consecutive machines washes at 30°C)		1.7	1.8	1.8	1.9	1.8	1.9
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4	4
		Dry	4	4	4	4	4	4
16	PH Value		7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8

		Z	AX	XY	CD	
1	Material	Outer side	Polyester	Polyester	Polyester	Polyester
		Filling material	Polyester	Polyester	Polyester	Polyester
2	Nature of Dye	Dope	Dope	Dope	Dope	
3	TOG Value (Clo Value)	2.9	3.6	2.7	3.0	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition
5	Wt of complete blanket	3.3 kg	3.6 kg	3.7 kg	3.8 kg	
6	Wt/sq mtr single layer	Filling material	321.5	244.4	285.5	279.8
7	Thickness (3 x layers) at 46 g wt (to be carried out before bailing)		6.3 - 6.7	4.9 - 5.7	6.2 - 7.0	6.5 - 7.5
8	Length		241 - 242	242 - 243	238 - 239	241 - 242
9	Width		169 - 170	166 - 167	169 - 170	167 - 168
10	Raising		One side raised	Both side raised	Both side raised	Both side raised
11	Tensile strength	One side	Av= 530N	Av= 500N	Av= 530N	Av= 440N
		Other side	Av= 170N	Av= 260N	Av= 240N	Av= 230N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.0	1.0	1.0
		Other side	1.0	0.5	1.5	1.0
13	Wt loss% (after 3 x consecutive machines washes at 30°C)		1.7	1.8	1.9	1.7
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4
		Staining on Cotton	4	4	4	4
		Staining on Polyester	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4
		Dry	4	4	4	4
16	PH Value		7 - 8	7 - 8	7 - 8	7 - 8

RA-I M Mosa
 Checked by (Naeem Nasir)

Bilal
 Bilal International

Nexus
 Nexus Trading (Imran Maqbool)

RA-I Global
 I/C Lab



ARMY STORES INSPECTION DEPOT LAHORE



LAB TEST REPORT

Page 1 of 4

Nomenclature	Fleece Blanket 2 ply	Ref: No. 4219/ LAB/LID/
F/Note No.	F.3(9)/2024-25/NDMA (Proc) Dated 07-02-2025	
Nature of Sample	Outer Agency	Temp= 21°C
		Humidity= 65%
Date Receipt	18-02-2025	Date of Reporting
No of Sample	31 Nos	___ Apr 2025
Client Name:	M/S NDMA	

S#	DESCRIPTION	Results						
		AA	AB	AE	AF	AG	AI	
1	Material	Polyester	Polyester	Polyester	Polyester	Polyester	Polyester	
2	Nature of Dye	Dope	Disperse	Disperse	Dope	Dope	Dope	
3	TOG Value (Clo Value) 3-4	1.78	1.58	1.75	1.71	1.80	1.78	
4	Fire Resistance Resistance to cigarette (ISO 12952-1&2) Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	
		No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition	
5	Wt of complete blanket 2-2.2Kgs	2.1 kg	2.2 kg	2.2 kg	2.6 kg	2.2 kg	2.1 kg	
6	Wt/sq mtr single layer	245.5	267.0	260.3	311.2	248.3	239.7	
7	Thickness (2 x layers) at 46 g wt (to be carried out before bailing)	4.9 - 5.2	5.4 - 5.6	5.5 - 5.7	6.7 - 7.1	5.5 - 5.9	5.7 - 6.0	
8	Length 240 +1cm	248 - 249	237 - 239	236 - 238	241 - 243	249 - 250	240 - 241	
9	Width 165 +1	177 - 178	165 - 166	165 - 166	169 - 170	176 - 177	165 - 166	
10	Raising	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	
11	Tensile strength 250N	One side	Av= 580N	Av= 600N	Av= 700N	Av= 410N	Av= 590N	Av= 500N
		Other side	Av= 360N	Av= 240N	Av= 290N	Av= 210N	Av= 280N	Av= 270N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.5	1.0	1.0	1.5	1.0
		Other side	1.5	0.5	1.5	1.0	1.5	1.0
13	Wt loss% (after 3 x consecutive machines washes at 30°C)	1.9	1.8	1.9	1.8	1.9	1.8	
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4	4
		Dry	4	4	4	4	4	4
16	PH Value	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	

RA-I
Checked by
(Naem Nasir)

RA-I
I/C Lab
(Imran Maqbool)



ARMY STORES INSPECTION DEPOT LAHORE



Quality Contractors
Arneca International
Nadir Saidjan

S#	DESCRIPTION	Results					
		AL	AO	BC	BD	BE	
1	Material	Polyester	Polyester	Polyester	Polyester	Polyester	
2	Nature of Dye	Dope	Disperse	Dope	Dope	Dope	
3	TOG Value (Clo Value)	1.74	1.75	1.60	1.75	1.85	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
5	Wt of complete blanket	2.5 kg	2.2 kg	2.7 kg	2.8 kg	2.2 kg	
6	Wt/sq mtr single layer	299.7	259.2	232.0	326.0	244.7	
7	Thickness (2 x layers) at 46 g wt (to be carried out before bailing)	7.5 - 7.8	5.3 - 6.1	6.9 - 7.2	5.2 - 5.5	4.6 - 5.4	
8	Length	241 - 242	236 - 237	242 - 243	247 - 248	248 - 252	
9	Width	168 - 170	167 - 168	166 - 167	168 - 169	175 - 176	
10	Raising	Both side raised	Both side raised	Both side raised	One side raised	Both side raised	
11	Tensile strength	One side	Av= 470N	Av= 760 N	Av= 520N	Av= 860N	Av= 610N
		Other side	Av= 200N	Av= 280N	Av= 180N	Av= 250N	Av= 260N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.5	1.0	1.0	1.5	1.0
		Other side	1.0	0.5	0.5	0.5	1.0
13	Wt loss% (after 3 x consecutive machines washes at 30°C)	1.8	1.9	1.7	1.9	1.8	
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4
		Dry	4	4	4	4	4
16	PH Value	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	
		BF	BJ	BM	BQ	DA	
1	Material	Polyester	Polyester	Polyester	Polyester	Polyester	
2	Nature of Dye	Dope	Dope	Dope	Dope	Dope	
3	TOG Value (Clo Value)	1.78	1.75	1.78	1.91	1.70	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	No Ignition
5	Wt of complete blanket	2.3 kg	2.7 kg	2.1 kg	2.2 kg	2.3 kg	
6	Wt/sq mtr single layer	288.5	310.6	247.9	240.2	280.9	
7	Thickness (2 x layers) at 46 g wt (to be carried out before bailing)	7.1 - 7.2	6.9 - 7.6	5.1 - 5.6	5.5 - 5.9	6.6 - 7.2	
8	Length	241 - 242	238 - 239	240 - 241	248 - 249	241 - 242	
9	Width	162 - 163	171 - 172	169 - 170	165 - 166	163 - 164	
10	Raising	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	
11	Tensile strength	One side	Av= 620N	Av= 450N	Av= 310N	Av= 360N	Av= 450N
		Other side	Av= 170N	Av= 250N	Av= 260N	Av= 270N	Av= 220N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	0.5	1.0	0.5	1.5
		Other side	1.0	1.0	1.0	1.0	1.0
13	Wt loss% (after 3 x consecutive machines washes at 30°C)	1.8	1.9	1.8	1.9	1.7	
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4
		Dry	4	4	4	4	4
16	PH Value	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	

RA-I
Checked by
(Naeem Nasir)

Bataan Innovatik Nexos Shabbir Sons - Pak Business
RA-I
I/C Lab
(Imran Maqbool)



ARMY STORES INSPECTION DEPOT LAHORE



Page 3 of 4 Saleem Ali Dreding Hussain Saad M.M Musa
9cc

S#	DESCRIPTION	DE		Results			
		DE	DO	DX	CO	EF	
1	Material	Polyester	Polyester	Polyester	Polyester	Polyester	
2	Nature of Dye	Dope	Dope	Disperse	Dope	Dope	
3	TOG Value (Clo Value)	1.71	1.76	1.75	1.65	1.18	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	
5	Wt of complete blanket	2.4 kg	2.2 kg	2.2 kg	2.6 kg	2.1 kg	
6	Wt/sq mtr single layer	274.5	242.3	263.7	312.0	263.0	
7	Thickness (2 x layers) at 46 g wt (to be carried out before bailing)	6.3 - 6.6	5.3 - 5.8	5.2 - 5.4	6.3 - 6.8	6.8 - 7.2	
8	Length	235 - 238	247 - 249	240 - 241	242 - 243	240 - 241	
9	Width	164 - 165	177 - 178	163 - 164	167 - 168	171 - 172	
10	Raising	Both side raised	Both side raised	Both side raised	Both side raised	One side raised	
11	Tensile strength	One side	Av= 500N	Av= 640N	Av= 680N	Av=490 N	Av= 570N
		Other side	Av= 230N	Av= 290N	Av= 280N	Av= 210N	Av= 150N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.0	1.5	1.0	1.0
		Other side	1.5	1.0	1.0	1.5	1.0
13	Wt loss% (after 3 x consecutive machines washes at 30°C)	1.8	1.6	1.8	1.7	1.9	
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4
		Dry	4	4	4	4	4
16	PH Value	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	

S#	DESCRIPTION	EG		FJ			
		GI	GO	HX			
1	Material	Polyester	Polyester	Polyester	Polyester	Polyester	
2	Nature of Dye	Dope	Dope	Dope	Dope	Dope	
3	TOG Value (Clo Value)	1.70	1.69	1.78	1.76	1.82	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	
5	Wt of complete blanket	2.6 kg	2.3 kg	2.2 kg	2.1 kg	2.2 kg	
6	Wt/sq mtr single layer	298.0	284.3	247.5	238.6	236.4	
7	Thickness (2 x layers) at 46 g wt (to be carried out before bailing)	7.9 - 8.2	6.5 - 7.0	5.2 - 5.6	5.3 - 5.7	5.2 - 5.9	
8	Length	248 - 249	242 - 244	242 - 243	241 - 242	248 - 250	
9	Width	165 - 166	167 - 168	167 - 168	168 - 169	177 - 178	
10	Raising	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	
11	Tensile strength	One side	Av= 580N	Av= 810N	Av= 520N	Av= 400N	Av= 510N
		Other side	Av= 230N	Av= 200N	Av= 280N	Av= 260N	Av= 270N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.5	1.5	1.0	1.5
		Other side	1.0	1.0	1.5	1.0	1.0
13	Wt loss% (after 3 x consecutive machines washes at 30°C)	1.7	1.6	1.8	1.9	1.8	
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4
		Dry	4	4	4	4	4
16	PH Value	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	

Checked by (Naeem Nasir)
Cops Enterprise
Dak RASC
FTS
The Trade
RA-I USman
I/C Lab
(Imran Maqbool)



ARMY STORES INSPECTION DEPOT LAHORE



Awar Global Active Vision zeby Cox Zehra Tariq
 Page 4 of 4

		OO	OM	XA	XX	YY	
1	Material	Polyester	Polyester	Polyester	Polyester	Polyester	
2	Nature of Dye	Dope	Dope	Dope	Dope	Dope	
3	TOG Value (Clo Value)	1.79	1.65	1.73	2.0	1.77	
4	Fire Resistance	Resistance to cigarette (ISO 12952-1&2)	No Ignition	No Ignition	No Ignition	No Ignition	
		Resistance to flame (ISO 12952-3&4)	No Ignition	No Ignition	No Ignition	No Ignition	
5	Wt of complete blanket	2.2 kg	2.5 kg	2.4 kg	2.2 kg	3.1 kg	
6	Wt/sq mtr single layer	233.9	284.9	299.2	247.6	263.8	
7	Thickness (2 x layers) at 46 g wt (to be carried out before bailing)	5.7 - 5.9	5.8 - 6.0	6.8 - 7.0	4.9 - 5.6	6.4 - 6.9	
8	Length	242 - 243	246 - 247	241 - 242	245 - 248	238 - 239	
9	Width	165 - 166	163 - 164	160 - 161	167 - 168	163 - 164	
10	Raising	Both side raised	Both side raised	Both side raised	Both side raised	Both side raised	
11	Tensile strength	One side	Av= 360N	Av= 410N	Av= 650N	Av= 480N	Av= 490N
		Other side	Av= 280N	Av= 220N	Av= 200N	Av= 260N	Av= 250N
12	Shrinkage% (after 3 x consecutive machines washes at 30°C)	One side	1.0	1.0	1.5	1.5	1.5
		Other side	0.5	1.0	0.5	1.0	0.5
13	Wt loss% (after 3 x consecutive machines washes at 30°C)	1.9	1.8	1.7	1.9	1.8	
14	Dye Fastness to Washing No.2	Change in Shade	4	4	4	4	4
		Staining on Cotton	4	4	4	4	4
		Staining on Polyester	4	4	4	4	4
15	Dye Fastness to Rubbing	Wet	4	4	4	4	4
		Dry	4	4	4	4	4
16	PH Value	7 - 8	7 - 8	7 - 8	7 - 8	7 - 8	

RA-I
 Checked by
 (Naeem Nasir)

RA-I
 I/C Lab
 (Imran Maqbool)

ISO 9001 - 2015

Initially Compliant Firms

Anx C

Two Ply Blanket Firms

Ser	Firm Name
1.	M/s Maris Intl (Pvt) Ltd
2.	M/s Ali Trading Corporation
3.	M/s FTS International (Pvt) Ltd
4.	M/s Usman Traders
5.	M/s Blue Star International
6.	M/s Zeb & Company
7.	M/s Nadir Saidjan Industries
8.	M/s Awan Traders
9.	M/s The Trade
10.	M/s Shabbir & Sons
11.	M/s Bilal International Enterprises
12.	M/s Nexus Trading (Pvt) Ltd

Three Ply Blanket Firms

Ser	Firm Name
1.	M/s Ali Trading Corporation
2.	M/s FTS International (Pvt) Ltd
3.	M/s Usman Traders
4.	M/s Blue Star International
5.	M/s Zeb & Company
6.	M/s Nadir Saidjan Industries
7.	M/s Pak Rose Enterprises
8.	M/s Bilal International Enterprises

[Handwritten Signature]
24/4/25.

[Handwritten Signature]
24/4/25